

E 1950 000

E 1955 000

N 340 000

N 335 000

Beauty
CampMussel
Crossing

Beauty

30" SAMPLED				
SP. GR.	WT%	ASH	SUL	BTU
1.55	45.66	16.45	0.71	12632
1.60	50.50	17.67	0.70	12410
1.65	56.30	19.36	0.68	12110
SINK	100	36.34	0.67	9094

23" SAMPLED		
ASH	SUL	BTU
20.80	1.21	12051

30" SAMPLED		
ASH	SUL	BTU
36.34	0.67	9094

ASH SUL BTU		
26.64	0.61	10688

8" MIDDLE		
ASH	SUL	BTU
58.12	0.47	5709

31" TOP + BOTTOM		
ASH	SUL	BTU
19.13	0.64	12315

* 30 1/4" SAMPLED		
ASH	SUL	BTU
22.31	0.53	11631

23" TOP		
ASH	SUL	BTU
17.09	0.66	12439

21" BOTTOM		
ASH	SUL	BTU
17.35	0.60	12685

* 14 1/4" SAMPLED		
ASH	SUL	BTU
24.66	0.70	11339

LEGEND

COAL THICKNESS LINES

NO COAL	0'-12"
	12'-24"
	24'-36"
	36'-48"
	48'-60"

HIGHWALL
OUTCROP
DRILLHOLE
ROCK TO ROCK THICKNESS

COAL SECTIONS VERTICAL SCALE 1"=2'

COAL
PARTING
COAL AND SHALE

C&K SNOWSHOE AREA : 1 SEAM : BROOKVILLE COAL THICKNESS AND QUALITY

SCALE 1"=400' SJH 12-1989