

	SHAWMUT CLAY MANUFACTURING COMPANY							PRODUCTION STATISTICS						
	Six-way - 3 $\frac{1}{4}$ " Bore							Nine-way - 3 $\frac{1}{4}$ " Bore						
1929	Pressing Duct Feet	Setting Duct Feet	Drier Loss Duct Feet	% of Drier Loss	Drawing W.E. Insp. Duct Feet	Burning Loss Duct Feet	% of Burning Loss	Pressing Duct Feet	Setting Duct Feet	Drier Loss Duct Feet	% of Drier Loss	Drawing W.E. Insp. Duct Feet	Burning Loss Duct Feet	% of Burning Loss
Jan.	305,614	262,180	43,434	.142	258,732	3,448	.013	89,873	71,081	18,792	.209	56,187	14,894	.209
Feb.	253,008	235,980	17,028	.067	174,816	61,164	.259	52,479	46,737	5,742	.109	41,406	5,331	.114
Mar.	335,354	320,252	15,102	.045	263,495	56,757	.178	17,362	14,905	2,457	.141	13,925	3,437	.23
Apr.	365,082	348,690	16,392	.044	205,834	142,856	.409	64,368	51,381	12,987	.201	10,530	40,851	.795
May	386,234	354,320	31,914	.082	263,232	91,088	.257	131,328	95,202	36,126	.275	83,322	11,880	.124
June	390,190	370,946	19,244	.049	308,655	62,291	.167	117,504	101,979	15,525	.132	75,915	26,064	.255
July	490,652	460,582	30,070	.061	319,520	141,062	.306	175,232	154,548	20,684	.118	99,171	55,377	.358