

SHAWMUT CLAY MANUFACTURING COMPANY

PRODUCTION STATISTICS

Four-way - 4 $\frac{1}{4}$ " BoreSix-way - 4 $\frac{1}{4}$ " Bore

1929	Pressing Duct Feet	Setting Duct Feet	Drier Loss Duct Feet	% of Drier Loss	Drawing W.E.Insp. Duct Feet	Burning Loss Duct Feet	% of Burning Loss	Pressing Duct Feet	Setting Duct Feet	Drier Loss Duct Feet	% of Drier Loss	Drawing W.E.Insp. Duct Feet	Burning Loss Duct Feet	% of Burning Loss
Jan.	-	-	-	-	-	-	-	-	-	-	-	-	-	-
Feb.	-	-	-	-	-	-	-	-	-	-	-	-	-	-
Mar.	-	-	-	-	-	-	-	-	-	-	-	-	-	-
Apr.	35,532	33,060	2,472	.069	28,284	4,776	.144	-	-	-	-	-	-	-
May	-	-	-	-	-	-	-	-	-	-	-	-	-	-
June	-	-	-	-	-	-	-	-	-	-	-	-	-	-
July	-	-	-	-	-	-	-	306	306	-	-	-	-	-